



vestige

DUPLE-15

Very high-precision addition silicone for models duplication in dental laboratories. Final hardness 15 Shore "A".

Description / Use

Liquid vinylpolysiloxane for duplication in laboratories. Extremely accurate in the reproduction of the surface models, the silicone is provided with high elastic recovery and tear resistance. After the polymerization, the silicone maintains overtime its dimensional stability. It is particularly suitable for models which have prominent overcuts. Colour: pink.

Standard packaging REF 1L6000

VESTIGE DUPLÉ 15: 2x1Kg bottles (base+catalyst)

Standard packaging REF 1L6010

VESTIGE DUPLÉ 15: 2x5Kg cans (base+catalyst)

Characteristics

- Mixing ratio 1:1
- Fluid
- High mechanical resistance
- Dimensional stability
- Compatible
- Precise

Advantages

- Easy to measure out
- Vacuum mixing not required
- It does not deform during the templates removal
- Unaltered in time restorations, even after weeks
- Tested on dental stones, coatings and resins
- Clear reproduction of details

TECHNICAL DATA	VESTIGE DUPLÉ 15
Mixing ratio	1:1
Mixing time (23°C)	1'
Total working time (23°C)	5'
Setting time (23°C)	30'
Hardness	15 Shore "A"
Linear dimensional change	< 0,05%